HA 0700 GP

Technical Data Sheet

Polypropylene, Homopolymer



Product Description

HA 0700 GP is a high molecular weight polypropylene homopolymer resin, with good stiffness and impact resistance, developed for extrusion applications.

HA 0700 GP is non-phthalate grade.

Typical customer applications are extrusion of sheets, profiles and non-pressure pipes.

Product Characteristics

Application Sheet and Non-Pressure Pipe Extrusion. Thermoforming

Processing Method Extrusion

Market Consumer Products. Rigid Packaging

Features High Molecular Weight. Good Impact Properties. Good Stiffness

Broad MWD. Non-Phthalate

	Nominal		
Typical Properties	Value	Units	Test Method
Physical			
Melt Flow Rate (230°C/2.16kg) Mechanical	0.75	g/10 min	ISO 1133
Flexural modulus (2 mm/min)	1500	MPa	ISO 178
Tensile modulus (1 mm/min)	1450	MPa	ISO 527
Tensile Strength at Yield (50 mm/min)	32	MPa	ISO 527
Elongation at Yield (50 mm/min)	11	%	ISO 527
Impact			
Charpy Impact Strenght (Notched, 23°C)	7.5	kJ/m ²	ISO 179
Izod Impact Strenght (Notched, 23°C) Thermal	8.5	kJ/m ²	ISO 180
Vicat Softening Temperature (10N)	155	°C	ISO 306
Heat Deflection Temperature (0.45 MPa)	93	°C	ISO 75B

Notes

These are typical property values not to be construed as specification limits

REACH

Polypropylene are exempted from registration under REACH. However, the corresponding monomers (used as raw materials for polymer production) and production) and relevant additives have been registered. Please see related Declaration of Compliance for Plastic Food Contact Materials (DoC for PFCM).

Packaging

Polypropylene pellets is typically packed in polyethylene bags with net weight of 25kg each. 50 bags are stacked on a flat wooden pallet (dimensions: 1100mm x 1300mm x 150mm) with net weight of 1250kg per pallet that is stretch-hood film wrapped. Upon agreement with a customer PP pellet can be packed into big bag sized for 1000kg on wooden pallet (dimensions: 1140mm x 1140mm x 150mm) without stretch-hood film wrapping.

Storage

Polypropylene packed 25kg bags 1000kg product in big bags stacked wooden pallet shall stored on be preventing enclosed dry place from direct sunlight from at least meter far heaters, at temperature min. -15°C / max. 35°C, relative humidity max. 80%. Prior to processing PP product bags shall be kept in production area for at least 12 hours.

PP shelf life is 36 months from the date of manufacture.

SOCAR Polypropylene Technical Data Sheet SOCAR Polymer Date: 10/1/2021