HB 2500 GP

Technical Data Sheet

Polypropylene, Homopolymer



Mominal

Product Description

HB 2500 GP is a homopolymer polypropylene used by customers for injection moulding applications. It exhibits a high fluidity combined with a good stiffness.

HB 2500 GP is non-phthalate grade. This product is suitable for food contact.

Product Characteristics

Application General Purpose. Furniture. Housewares

Processing Method Compounding. Injection Molding

Market Consumer Products

Features High Flow. Medium Stiffness. Homopolymer

Phthalate-Free

	Nominai		
Typical Properties	Value	Units	Test Method
Physical			
Melt Flow Rate (230°C/2.16kg) Mechanical	25	g/10 min	ISO 1133
Flexural modulus (2 mm/min)	1400	MPa	ISO 178
Tensile modulus (1 mm/min)	1350	MPa	ISO 527
Tensile Strength at Yield (50 mm/min)	32	MPa	ISO 527
Elongation at Yield (50 mm/min) Impact	10	%	ISO 527
Charpy Impact Strenght (Notched, 23°C)	2.0	kJ/m ²	ISO 179
Izod Impact Strenght (Notched, 23°C) Thermal			ISO 180
Vicat Softening Temperature (10N)	154	°C	ISO 306
Heat Deflection Temperature (0.45 MPa)	90	°C	ISO 75B

Notes

These are typical property values not to be construed as specification limits

REACH

Polypropylene are exempted from registration under REACH. However, the corresponding monomers (used as raw materials for polymer production) and production) and relevant additives have been registered. Please see related Declaration of Compliance for Plastic Food Contact Materials (DoC for PFCM).

Packaging

Polypropylene pellets is typically packed in polyethylene bags with net weight of 25kg each. 50 bags are stacked on a flat wooden pallet (dimensions: 1100mm x 1300mm x 150mm) with net weight of 1250kg per pallet that is stretch-hood film wrapped. Upon agreement with a customer PP pellet can be packed into big bag sized for 1000kg on wooden pallet (dimensions: 1140mm x 1140mm x 150mm) without stretch-hood film wrapping.

Storage

Polypropylene 1000kg packed 25kg bags stored product in big bags stacked wooden pallet shall on be enclosed dry place preventing from direct sunlight at least from meter far heaters, at temperature Prior to processing PP product bags shall be kept in production area min. -15°C / max. 35°C, relative humidity max. 80%. for at least 12 hours.

PP shelf life is 36 months from the date of manufacture.

SOCAR Polypropylene Technical Data Sheet SOCAR Polymer Date: 10/4/2021