RB 3545 MO

Technical Data Sheet Polypropylene, Random Copolymer with Ethylene

Product Description

RB 3545 MO is a polypropylene random copolymer for injection molding with clarifier, antistatic, and molding release additivation.

RB 3545 MO offers a very good flowability and an exellent transparency.

Typical applications of RB 3545 MO is thin walled packaging with high transparency.

Product Characteristics

Application	Caps & Closures. Containers. Housewares.
Processing Method	Injection Molding. TWIM
Market	Consumer Products. Rigid Packaging
Features	High Transparency. High Flow. Good Impact. Clarifier. Antistatic. Molding Release

	Nominal		Test Method
Typical Properties	Value	Units	
Physical			
Melt Flow Rate (230°C/2.16kg)	40	g/10	ISO 1133
Mechanical			
Flexural modulus (2 mm/min)	1000	MPa	ISO 178
Tensile modulus (1 mm/min)	950	MPa	ISO 527
Tensile Strength at Yield (50 mm/min)	25	MPa	ISO 527
Elongation at Yield (50 mm/min)	13	%	ISO 527
Impact			
Izod Impact Strenght (Notched, 23°C)	5.2	kJ/m ²	ISO 180
Izod Impact Strenght (Notched, -20°C)	2.1	kJ/m ²	ISO 180
Thermal			
Vicat Softening Temperature (10N)	127	°C	ISO 306
Heat Deflection Temperature (0.45 MPa)	70	°C	ISO 75B
Optical			
Haze	27	%	ASTM D1003
Clarity	75	%	ASTM D1003

Notes

These are typical property values not to be construed as specification limits

REACH

Polypropylene are exempted from registration under REACH. However, the corresponding monomers (used as raw materials for polymer production) and relevant additives have been registered. Please see related Declaration of Compliance for Plastic Food Contact Materials (DoC for PFCM).

Packaging

Polypropylene pellets is typically packed in polyethylene bags with net weight of 25kg each. 50 bags are stacked on a flat wooden pallet (dimensions: 1100mm x 1300mm x 150mm) with net weight of 1250kg per pallet that is stretch-hood film wrapped. Upon agreement with a customer PP pellet can be packed into big bag sized for 1000kg on wooden pallet (dimensions: 1140mm x 150mm) without stretch-hood film wrapping.

Storage

Polypropylene product packed in 25kg 1000kg big stacked pallet shall bags or bags on wooden be stored least 1 in enclosed dry place preventing from direct sunlight at meter far from heaters, at temperature min. -15°C / max. 35°C, relative humidity max. 80%. Prior to processing PP product bags shall be kept in production area for at least 12 hours.

PP shelf life is 36 months from the date of manufacture.

SOCAR Polypropylene Technical Data Sheet SOCAR Polymer Date: 9/21/2021